

# SRS Ersolan

## Industrial Gear Oils



March 2024

### Characteristics

**SRS Ersolan** are zinc-free, industrial gear oils blended exclusively from highly solvent refined paraffinic base oils from Salzbergen and Hamburg refineries. SRS Ersolan industrial gear oils ensure maximum wear protection, oxidation stability, protection against corrosion, good thermal stability, prevention of pitting, excellent demulsibility, compatibility with seals and non-ferrous metals, negligible foam tendency.

### Application

**SRS Ersolan** gear oils, available in different viscosity grades, are recommended for a wide variety of industrial gear drives. They have proven themselves in operation in numerous transmissions from many different manufacturers. SRS Ersolan industrial gear oils have shown their excellent performance characteristics in a particularly impressive manner in thermally-stressed gear drives and under difficult operating conditions in mining and steel industry.

### Performance / Specifications

The requirements for CLP gear oils as described in DIN 51 517 Part 3 and SEB 181 226 are met. Many of the requirements of these two standards are outperformed by far. SRS Ersolan is approved by VDEh. SRS Ersolan industrial gear oils meet the requirements of ISO 12925 part 1 / ISO 6743 part 6 L-CKC. Key Accounts have more stringent requirements than those defined by DIN and SEB. These demands like FE 8-test are also met.

### Approvals

- VDEh-Approval SEB 181 226
- ZF Approval Number ZF003462 / ZF003463  
ZF TE-ML 04H<sup>1</sup>
- Bundeswehr TL 9150 – 0105/4 <sup>2</sup>

<sup>1</sup> for SRS Ersolan 100 and SRS Ersolan 150

<sup>2</sup> for SRS Ersolan 150 and SRS Ersolan 320

SRS Ersolan industrial gear oils are products of the H&R ChemPharm GmbH.

| Typical Data                                 | Test Method      | SRS Ersolan |        |        |        |        |        |        |
|--|------------------|-------------|--------|--------|--------|--------|--------|--------|
|  |                  | 68          | 100    | 150    | 220    | 320    | 460    | 680    |
| Designation                                  | DIN 51 502       | CLP68       | CLP100 | CLP150 | CLP220 | CLP300 | CLP460 | CLP680 |
| Density at 15°C      g/cm <sup>3</sup>       | DIN EN ISO 12185 | 0.877       | 0.881  | 0.887  | 0.891  | 0.893  | 0.897  | 0.900  |
| Kin. Viscosity at 40°C   mm <sup>2</sup> /s  | DIN EN ISO 3104  | 69          | 102    | 154    | 223    | 321    | 449    | 686    |
| Kin. Viscosity at 100°C   mm <sup>2</sup> /s | DIN EN ISO 3104  | 8.5         | 11.2   | 14.3   | 18.8   | 23.7   | 29.2   | 39     |
| Flash Point COC      °C                      | DIN ISO 2592     | 235         | 245    | 250    | 285    | 290    | 295    | 300    |
| Pour Point              °C                   | DIN ISO 3016     | -24         | -21    | -21    | -21    | -18    | -15    | -15    |
| FZG-Test A/16.6/140   Fail stage             | DIN ISO 14635    | > 12        | > 12   | > 12   | > 12   | > 12   | > 12   | > 12   |

The above values may vary within the commercial limits.

**Made in Germany**